

Accura® Xtreme Plastic

for use with solid-state stereolithography (SLA®) systems

# Get extreme performance and durability with Accura® Xtreme Plastic.



## **APPLICATIONS**

- Form, fit and function prototypes
- Durable Assemblies
  - Snap fit assemblies
  - Tough enclosures
  - Consumer electronic components
- Master patterns for RTV/Silicone moulding
- Replace CNC machining of Polypropylene and ABS

## **FEATURES**

- Look and feel of a durable moulded plastic
- Outstanding durability and impact resistance
- Thermal resistance over 60° C
- Easy to use low viscosity formulation
- Fully developed and tested build styles

## **BENEFITS**

- Increased application opportunities
- Suitable for assemblies and functional testing
- Prototypes withstand modest temperatures without distortion
- Faster recoating and build times
- Maximise reliability with no user R&D

## **3D SYSTEMS**

TRANSFORM YOUR PRODUCTS

# Accura® Xtreme Plastic

For use with solid-state stereolithography (SLA®) systems





## **TECHNICAL DATA**

Liquid Material			
MEASUREMENT	CONDITION	VALUE:	
Appearance		Grey	
Liquid Density	@ 25 °C (77 °F)	1.13 g/cm <sup>3</sup>	
Solid Density	@ 25 °C (77 °F)	1.19 g/cm <sup>3</sup>	
Viscosity	@ 30 °C (86 °F)	250 - 300 cps	
Penetration Depth (Dp) *		4.1 mils	
Critical Exposure (Ec) *		11.7 mJ/cm <sup>2</sup>	
Tested Build Styles		EXACT™	

## **Post-Cured Material**

MEASUREMENT	CONDITION	VALUE:
Tensile Strength	ASTM D 638	38 - 44 MPa (5510 - 6380 PSI)
Tensile Modulus	ASTM D 638	1790 - 1980 MPa (260 - 287 KSI)
Elongation at Break (%)	ASTM D 638	14 - 22 %
Flexural Strength	ASTM D 790	52-71 MPa (7540 - 10300 PSI)
Flexural Modulus	ASTM D 790	1520 - 2070 MPa (220 - 300 KSI)
Impact Strength (Notched Izod)	ASTM D 256	35 - 52 J/m (0.66 - 0.98 ft-lb/in)
Heat Deflection Temperature	ASTM D 648 @ 0.45 MPa (66 PSI) @ 1.82 MPa (264 PSI)	62 °C (144  °F) 54 °C (129 °F)

· Dp/Ec values are the same on all solid-state laser SLA® systems.



### 3D Systems Europe Ltd.

Mark House, Mark Road Hemel Hempstead Herts HP2 7UA - UK www.3dsystems.com Tel: (+44) 1442 282 600 Fax: (+44) 1442 282 601 marketing.uk@3dsystems.com Nasdaq: TDSC

#### **3D Systems GmbH**

Postfach 12 02 07 D-64239 Darmstadt Germany

Tel: (+49) 6151 357 0 Fax: (+49) 6151 357 333 info@3dsystems-europe.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

TRANSFORM YOUR PRODUCTS

© 2007 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. EXACT and FAST are trademarks, and the 3D logo, Accura and SLA are registered trademarks of 3D Systems, Inc.